

LUKOR

HIGH DENSITY POLYETHYLENE

Product Quality Index	Test method	Unit	HXF 4810 H
Density	ASTM D1505	g/cm ³	0,946-0,950
Melt index, 190/21.6	ASTM D1238	g/10 min	7-13
Film appearance		relative units	20
Tensile strength at yield, min	ASTM D882	Mpa	18
Tensile strength at break, min.	ASTM D882	Mpa	30
Elongation at break, min.	ASTM D882	%	550
Application:	LUKOR HXF - 4810 H is used for shopping bags, thin films, sack liners and sheets.		

HXB 4810 H
High molecular weight hexene copolymer
Unipol process
Produced by JSC Lukor Ltd Kalush

Unipol is a registered trademark of Union Carbide Corporation

STAVROCHEM CO. LTD.
1022 BUDAPEST BÉG U. 3-5.
PHONE: +36 1 346-0670, FAX: +36 1 326-9259
E-MAIL: OFFICE@STAVROCHEM.HU
WWW.STAVROCHEM.HU